

TEST REPORT

THERMAL MEASUREMENT LABORATORY

School of Computing, Science & Engineering
Newton Building, The University of Salford
Salford, M5 4WT, England.

Tel: 0161 295 5172 or 3114 or 4406

Fax: 0161 295 4442

UKAS Testing
No. 1660
CPD Notified Laboratory
No. 1145



Date of Issue : 2 Apr, 2007
Your Order No. : Ash Ashfaq
Internal Reference No.: TT07/128

Signatory: **Dr.A.Simpson**

Page 1 of 3 pages

THERMAL RESISTANCE OF PLASTERBOARD COATED WITH THERMOZONE CEILING PAINT AND AIR SURFACE RESISTANCE LAYER

Client Thermozone Ltd., 7 109 Equilibrium, Huddersfield, HD3 3GE, UK

1. Sample 9.5 mm nominal thickness plasterboard coated with Thermozone Ceiling Coating Sample + 25mm air surface of resistance layer.

Product Standard applicable to tested specimens - N/A

2. Method Single specimen heat flow meter method. Heat flux direction – vertically downwards. Apparatus HFM1. The apparatus was calibrated against UKAS accredited EN 12667 guarded hot plate apparatus. Edge heat losses reduced by 125 mm edge insulation

3. Thermal Resistance of coated plasterboard and air surface resistance

Air Temperature °C	Warm Plasterboard Surface Temperature °C	Cold Plasterboard Surface Temperature °C	Thermal Resistance Plasterboard/Surface m ² K/W
25.36	18.52	13.84	0.166 ± 3%

TEST REPORT

Internal Reference No.: TT07/128

Page 2 of 3 pages

Thermal Measurement Laboratory, University of Salford

4. Test Details

Value For Specimen As-Tested

Initial specimen thickness	m	0.0100
Relative thickness change during test	%	-0.44
Dimensions	m	0.305 x 0.305
Relative volume change during test	%	-0.44
Mass before test	g	632.3
Mass after test	g	632.7
Relative mass change during test	%	0.06
Relative mass change during drying	%	N/A
Relative mass change during conditioning	%	0.03
Density of conditioned plasterboard as tested	kg/m ³	660.8
Temperature of Air	°C	24.36
Temperature of painted plasterboard surface (warm)	°C	18.52
Temperature of cold plasterboard surface	°C	13.84
Temperature drop across plasterboard/air surface	K	10.52
Temperature drop across plasterboard	K	4.68
Temperature drop across air surface layer	K	6.84
Density of heat flow rate	W/m ²	74.2
Thermal Resistance of plasterboard/air surface	m ² K/W	0.166
Thermal Resistance of plasterboard & paint	m ² K/W	0.063
Thermal Resistance of air surface layer	m ² K/W	0.103
Date of completion of the test		2 April 2006
Duration of test	hrs	48
Ambient temperature surrounding the apparatus during the test	°C	23

TEST REPORT

Internal Reference No.: TT07/128

Page 3 of 3 pages

Thermal Measurement Laboratory, University of Salford

5. Temperature Sensors

The temperature difference was determined by measuring the temperature of each surface with Chromel/Alumel (K type) thermocouples.

6. Thickness Measurement

The mean thickness of the plasterboard was determined by measuring the thickness at each corner and the centre edge with vernier calipers, before and after test.

7. Method and temperatures of conditioning

The specimen was conditioned for 23°C and 50% RH to constant mass before testing.

8. Errors in measured property

The maximum expected error in the measured thermal resistance of plasterboard/ air surface layer is within 3.0 %.

The measurement repeatability during the last 24 hours of thermal equilibrium was < 0.3%

9. The Experimental System

An identical plasterboard panel to that used in Report No.TT04/134 was coated with Thermozone Roof Coating Sample by the client. This was instrumented with thermocouples, as well as a thin calibrated heat flow meter. The painted face of the panel faced a matt black plate heat source positioned 50 mm above the panel. The air temperature was measured by thermocouples sited within the 50 mm air gap, at a distance of 25 mm above the painted face of the panel.

10. Name of Test Operator/s

A. Simpson

11. Thermal Energy Savings

The increase in thermal resistance with 9.5 mm nominal thickness plasterboard coated with Thermozone Ceiling Paint sample, over that for plain spray painted plasterboard (Report TT 04/134, $R = 0.136 \text{ m}^2\text{K/W}$) is 22 %.